



PRODUCT DATA SHEET

POLYSCRIM – VENTING LINER

PRODUCT DESCRIPTION

Description: A low-density extrusion coated film on one side of a white reinforced Kraft paper

FDA Status: None

RECOMMENDED STORAGE CONDITIONS

The material should be stored in well-ventilated area (temp. 60° - 80°F; RH – 40% - 60%). Avoid storing over extended periods. Avoid contamination.

PHYSICAL AND CHEMICAL PROPERTIES

- 1. **Color** White
- 2. **Thickness, mils**
 - a) Overall 3.7 - 4.5
 - b) Polyethylene 1.9 - 2.3
 - c) Paper 1.8 - 2.2
- 3. **Basis Wt. Lbs./Ream 3000 ft.²**
 - a) Overall 60.0 - 70.0
 - b) Coating (PE + Glass Scrim) 28.5 - 31.5
 - c) Paper 31.5 - 38.5
- 4. **Pinholes, No./yd²** <6.0
- 5. **Gas Transmission: cc/cin²/24hrs/1atm**
 - a) Oxygen NA
- 6. **Water Vapor Transmission**
 - a) gm/cin²/24hrs/100°F/90%RH 0.8 - 1.4
- 7. **Chemical Resistance Rating**
(Maximum Rating = 108)
 - a) Upright 95 - 105
 - b) Inverted 80 - 85

SUGGESTED PRODUCT USES

- Pool Aids
- Bleaches
- Hydrogen Peroxide 10%
- Starch Blends

Product applications listed above are a partial listing and do not cover all suitable applications. These are suggestions for general categories and user must test for suitability for their specific product.

PRODUCT NAME: POLYSCRIM – VENTING LINER
Rev. 051711

The technical information and suggestions for use made herein are based on SANCAP Liner research and experience and are believed to be reliable, but such information and suggestions do not constitute a warranty, and no patent liability can be assumed. Since SANCAP Liner has no control over the conditions under which the product is transported, stored, handled, used, or applied, buyer must determine for themselves, by preliminary tests or otherwise, the suitability of the product for their purposes. All products are sold subject to SANCAP Liner's written warranty, which is in lieu of all other warranties or merchantability and fitness for a particular purpose. SANCAP Liner's liability on any basis is limited to the price of the product used.